



KATILAC COATINGS INC.

Pureguard™

Formaldehyde-Free Pre-catalyzed Lacquer

A solvent-based system that is better for you and the environment



Pureguard™

Formaldehyde-Free Clear Pre-catalyzed Lacquer

KP Series PUREGUARD™ is a line of formaldehyde-free, HAPs-Free, solvent borne, one component, alkyd/amino resin based, clear pre-catalyzed lacquers. They are designed to be used in a self-sealing system but may also be used in conjunction with KCI's PURESEAL™ Formaldehyde-Free Vinyl Sealer. PUREGUARD™ is designed to be a greener drop-in replacement for most pre-catalyzed lacquer systems with little or no process or equipment changes.

These advanced products feature KCI's GreenCure™ technology; a unique cross-linking mechanism that does not contain or liberate formaldehyde during the drying or curing process. The Pure™ family of products meet LEEDS, GREENGUARD, IAQ and BIFMA standards for formaldehyde-free designation.

Features

- 31% weight solids; 27% volume solids
- HAPs Free, low odour, very user-friendly
- Meets green standards like LEEDS, Greenguard etc.
- Vastly exceeds NAAWS Performance Standard
- Self-sealing or with FK8 Pureseal™ Formaldehyde-Free Vinyl Sealer
- Available in 10, 20, 40, 90 degree sheens



Performance Testing

AWMAC / AWI (NAAWS Performance Standards Testing)

System #2 Pre-catalyzed Lacquers (Clear): KP Series score - 116/135 (standard 99/135)

Flammability Testing (ASTM E 84- 08a) Surface Burn Rating

Flame Spread Index.....5.0 Class 1 / Class A

Smoke Development.....5.0 Class 1 / Class A

(testing performed on concrete board by accredited independant laboratory)

KCMA Testing (ANSI/KCMA A161.1.1.2000)

- Chemical Testing (Vinegar, Lemon Juice, Orange Juice, Grape Juice, Ketchup, Coffee, Olive Oil, 100 Proof Alcohol, Mustard) – PASS; no signs of discolouration, blistering, swelling
- Detergent & Water Resistance Test – PASS; no signs of blistering, whitening, delamination, swelling
- Heat Resistance Test – PASS; no signs of discolouration, whitening, delamination or swelling
- Hot/Cold Cycle Test – PASS; 10 cycles with no signs of any film failure

Hot Print Resistance (ASTM D 2091-96)

72F (18 hrs) 4 psi - PASS; 120F (1 hr) 4 psi - PASS; 140F (1 hr) 4 psi - PASS

Hot/Cold Cycle Test (ASTM D 1211-97)

PASS 10 cycles

Household Chemical Resistance (ASTM D1308)

Distilled Water (D1308.6.1.1)	24 hrs	No effect
Ethyl Alcohol (D1308.6.1.3)	24 hrs	No effect
Coffee @ 180F (D1308.6.1.13)	24 hrs	No effect
Vinegar (D1308.6.1.4)	24 hrs	No effect
Mustard (D1308.6.1.12)	2 hrs	No effect
Vegetable Oil (D1308.6.1.11)	24 hrs	No effect
Dish Detergent (D1308.6.1.8)	24 hrs	No effect

Katilac Coatings Inc.

391 Hanlan Road, Unit 1
Woodbridge ON
t. 905-856-6464 | f. 905-856-6584
info@katilaccoatings.com

840 Appleby Line
Burlington ON
t. 905-637-2931 | f. 905-637-8918
orders@katilaccoatings.com



KATILAC COATINGS INC.

