



E16 OMNIPRIME™ Spray Ready Vinyl Modified Primer

E16 OMNIPRIME™ Spray Ready Vinyl Modified Primer is a solvent borne, pre-catalyzed alkyd/amino resin based white primer. It exhibits fast dry, high fill, and incredible sanding. It is designed to provide a highly filled smooth surface on MDF. E16 OMNIPRIME™ can be used in conjunction both pre-catalyzed and post-catalyzed pigmented topcoats as part of a high-quality interior wood finishing system.

SUGGESTED APPLICATIONS

- Interior trim and millwork
- Household furniture
- Cabinets

KEY PERFORMANCE FEATURES

- Spray ready
- Easy sanding
- Fast dry
- Excellent flow and leveling
- Incredible filling properties
- Excellent MDF adhesion
- Excellent chemical and moisture resistance

PHYSICAL PROPERTIES

Available Sheens	n/a
Weight Solids	45% ± 2
Volume Solids	32% ± 2
Viscosity	40-45" @ 25°C Ford 4
Specific Gravity	1.1500 ± 0.01 gms/cc @ 25°C
VOC	637 g/l
Typical coverage	10-12 m ² / ltr @ 1 mil dry

ADDITIONAL CHARACTERISTICS

Catalyzation	n/a
Pot-Life	n/a
Reduction	Not Required
Clean-up	CA4420 Gun Wash
Shelf-life	1 year from date of manufacture

Dry Times

26°C (~78°F) 50% RH	
To Touch	10 minutes
To Sand	30-60 minutes
To Stack/Pack	24 hours

Note: Drying times will decrease at higher temperatures/lower humidity and will increase at lower temperatures/high humidity

COATING PREPARATION - Ensure product is stirred well and brought to room temperature before use. Product may be sprayed by conventional, airless and air-assisted airless spray. E16 OMNIPRIME™ Spray Ready Vinyl Modified Primer does not require reduction. T4409 Lacquer Thinner can be used 5-10% by weight if desired.

SURFACE PREPARATION - Wood surface should be clean, dry and free from any oil or grease. Sand surface smooth with 150-180 grit sand paper. For easier primer application, seal routed MDF areas with a Katilac pre-catalyzed sealer or topcoat. Allow to dry 30-60 minutes at room temperature and sand coated areas with 240-320 grit sand paper. Then apply E16 OMNIPRIME™.

APPLICATION - This product is designed to be applied in ambient conditions of 12-32°C (~55-90°F) and below 50% relative humidity.

Apply product in full uniform coats ideally applied at a rate of 4 to 5 mils wet. Total film thickness of the finished system should not exceed 4 dry mils.

Coating should be thoroughly dried and sanded smooth before application of the topcoat. Sand with 240-320 grit professional finishing stearated, silicon carbide sandpaper. Proper sanding is critical to produce a smooth finish and promote adhesion between the primer and the topcoat.

SAFETY - During application, always wear eye protection, gloves and appropriate work clothing to minimize contact. Use a respirator and safety glasses at all times when spraying. Explosion proof ventilation is required with special consideration for enclosed or confined areas. Use caution when handling flammable liquids and eliminate sources of ignition and uncovered containers from the work place. Vapours formed from this product may travel or be moved by air currents and ignited by pilot lights, light switches, other flames, smoking, sparks, heaters, electrical equipment, static discharges or other ignition sources at locations distant from the product.

E16 OMNIPRIME™ Spray Ready Vinyl Modified Primer (cont'd)

PERFORMANCE TESTING / FILM CHARACTERISTICS

All performance testing is based on a composite of ASTM, AWI, ANSI and KCMA Standards.

KCI's E16 OMNIPRIME™ Spray Ready Vinyl Modified Primer is made from the same high-quality resins found in KCI's pigmented topcoats. Using this product as a seal coat does not detract from the performance attributes of the overall system.

DISPOSAL - Disposal of chemicals and their solutions should be done according to local, provincial and federal regulations. Safety Data Sheets are available and should be consulted when handling products. These products are for industrial and professional use only; Application directions must be followed.

WARRANTY – Katilac Coatings Inc. warrants that its products are free from defects in manufacture for a period of one (1) year from date of purchase, if used prior to expiration date and applied and used in accordance with Katilac Coatings' most current published specifications applicable to such products. Katilac Coatings Inc. expressly disclaims all other warranties, express or implied, including the implied warranties of merchantability and fitness for purpose. Katilac Coatings Inc. disclaims all liability for incidental, consequential or indirect damages of any nature whatsoever. This warranty cannot be changed or modified whether by course of dealing, custom or trade or otherwise, unless agreed to in writing by Katilac Coatings Inc.



Ver08/22 Supersedes all previous versions.
© 2022 Katilac Coatings Inc